

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 903 372 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
01.12.2004 Bulletin 2004/49

(51) Int Cl.7: **C08K 5/00, C08K 5/20**
// (C08K5/00, 5:20, 5:3435,
5:5333)

(21) Application number: **98117816.3**

(22) Date of filing: **19.09.1998**

(54) Synergistic polyamide stabilization method

Synergistische Polyamidstabilisierungsmethode

Méthode synergistique pour la stabilisation de polyamide

(84) Designated Contracting States:
BE CH DE ES FR GB IT LI NL

(30) Priority: **23.09.1997 US 936008**

(43) Date of publication of application:
24.03.1999 Bulletin 1999/12

(73) Proprietor: **Clariant Finance (BVI) Limited**
Road Town, Tortola (VG)

(72) Inventors:
• **Sidqi, Mohamed**
68200 Mulhouse (FR)
• **Stoll, Klaus**
79589 Binzen (DE)
• **Malik, Jan**
68300 St. Louis (FR)

• **Webster, Joseph Renl**
Charlotte, NC 28277 (US)

(74) Representative: **D'haemer, Jan Constant**
Clariant International Ltd.,
Patents & Trademarks Div.,
Rothausstrasse 61
4132 Muttenz (CH)

(56) References cited:
EP-A- 0 430 650 DE-A- 4 233 973
DE-A- 19 537 140 US-A- 5 147 935

Remarks:

The file contains technical information submitted
after the application was filed and not included in this
specification

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 903 372 B1

Description

FIELD OF THE INVENTION

[0001] The invention pertains to methods to stabilize polyamide polymers.

BACKGROUND OF INVENTION

[0002] The service life of polyamides is dependent on (1) the raw materials used in the manufacturing process, (2) the additives used in stabilizing the polymer against damage brought about by melt-processing and (3) environmental weathering factors. A serious drawback to providing stabilization systems for polyamides lies in the fact that the maximum concentration of many additives is limited. Polyamides are heretofore regarded as poor in solvating additives, especially non-polar additives having relatively low molecular weight in relation to the polyamide polymer. The aesthetics of an article such as made by molding processes can be affected such as by migration, blooming or plate-out of the additives. On the other hand, manufacturers of polyamide-based molded and extruded goods strive to include low concentrations of additives for economic reasons.

[0003] Oxalic acid di-aryl anilides, formed on condensing the acid, partial ester or di-ester with one or two moles of aniline derivatives are known light stabilizers. Unsymmetrical oxalic acid dianilides are described, for example in U.S. Pat. No. 4,003,875.


[0004] U.S. Pat. No. 5,045,083 discloses polyamide, copper complex and oxanilide UV absorber.

[0005] U.S. Pat. No. 4,544,691 discloses stabilizer compounds containing UV-absorbing derivatives of oxanilide, benzalmalonates, α -cyanocinnamates and o-hydroxyphenylbenzotriazoles, having a reactive phenolic group(s). These additives are suggested for use with polymer coating materials.

[0006] U.S. Pat. No. 5,338,319 discloses a polyamide stabilization system containing a copper complex, and water soluble oxalic acid diaryl amide.


[0007] U.S. Patent No. 5,380,774 discloses a polyamide molding composition containing a hindered phenolic antioxidant, phosphite, hindered amine stabilizer and optionally a benzotriazole.

[0008] European Publication number EP 0379470 discloses compounds used to improve the dyeability of polyamide. The compounds include a compound containing a sterically hindered amine group, trimesic acid trialkylamide, pyromellitic acid tetra-alkylamide, triamino substituted triazine, a hydroxyl-reactive dyestuff. Compounds containing a sterically hindered amine group are preferably



where R is hydrogen, C₁₋₈ alkyl, C₁₋₈ alkoxy, or COR₅.

[0009] WIPO publication WO 97/43335 discloses a stabilizer for polyamide having the structure:



[0010] Polyamide polymers are characterized by high tensile strength, Young's modulus and abrasion resistance, however polyamides require stabilization against thermo-oxidative and photodegradation to sustain these properties in demanding use applications. Polyamides must accept lightfast dyeing systems in addition. Discoloration of the resin matrix is highly critical and may cause shade changes in colored articles, such as fibers and moldings of polyamide

polymers. Therefore, further improvement in the stabilization systems for these materials is desirable in end uses such as fibers, and generally in high temperature processing of polyamide melts.


[0011] The polyamide structure contains labile hydrogens and exerts reductive or basic properties which are problematic from the standpoint of colorants. For example, in polyamide, organic red dyes undergo significant loss of shade upon thermal processing at the typical melt processing temperatures for polyamide. It would be desirable to minimize the tendency of polyamide to exert this influence on dyes while at the same time protecting the polymer matrix from loss of the desired physical properties.

[0012] The evolution of polyamide stabilization systems has advanced from earlier recommended hindered phenolic types, for example Irganox® 1098, to a combination of an antioxidant and a benzotriazole, such as the combination of Irganox® 1098 with Tinuvin® 234, well established in the art. Lightfast and photochemically stable dyed polyamide fibers containing oxalic acid di-aryl amides with a copper complex are known, for example from the aforementioned U.S. Pat. No. 5,338,319. These are applied in aqueous dye baths. In contrast, the present invention is directed to additives which are dispersed within the polyamide matrix by melt-processing at high temperatures above the glass transition, as in extrudates or moldings. WO 97/43335 provides a stabilizer which can be added in the melt to polyamide and improves heat stability, light stability, chemical stability, and dye affinity, however improvements are still sought.

[0013] Highly synergistic stabilization systems for polyamides have been found which exhibit unexpected further improvements for polyamide. These systems exhibit significant technical and economic advantages, even at low effective additive concentrations.

SUMMARY OF INVENTION

[0014] In accordance with the fundamental aspect of the invention there is provided a process for stabilizing polyamide polymers against the damage effected by light, heat and/or oxidation, even without the use of copper complexes, by using specified additives which act synergistically in polyamides. The process comprises incorporating an additive system comprising from 0.01% to 1% of a sterically hindered phenyl phosphonite, from 0.05 to 5% of an oxanilide, preferably non-hydroxyl substituted, and from 0.05 to 5% of an aromatic di-carbonyl (ester)amide of the formula



under melt processing conditions with polyamide, and forming a uniform and intimate mixture, wherein the percentages represents grams of additives used per hundred grams of polymer.

[0015] The weight ratio of phosphonite to oxanilide is from 1:5 to 5:1, preferably 1:5 to 1:1, and most preferably 1:5 to 1:3

[0016] The invention defines the basis, furthermore, for the effective and unexpected improved efficiency in the use of organic colorants with polyamide, such as solvent soluble, or polymer soluble organic dyes, for example, acid dispersed dyes, azo and diazo dyes, phthalocyanine blues and greens, diarylide yellows, perylenes, quinacridone, and the like. Therefore another aspect of the invention is a colored manufactured article such as a molding, extruded article or fiber of polyamide containing the additive system as defined above, in combination with one or more organic colorants.

DETAILED DESCRIPTION OF INVENTION


[0017] Polyamides stabilized according to the invention include the synthetic aliphatic, semi-aromatic and aromatic polyamides. Examples include nylon 6, nylon-6.6, nylon-6.10, nylon 6.11, nylon-6.12, nylon 11, nylon 12, and copolymers such as nylon-6.6/6, nylon-6.6/6.10, 6/11, 6/12; polyether-polyamide block copolymers, poly(m-phenyleneisophthalamide), poly(p-phenyleneterephthalamide), and the like all of which are commercially available from a variety of sources. The method includes using the stabilization system with formulated polyamides, including conventional impact toughened polyamide, and reinforced polyamides containing glass fiber, mineral and glass/mineral combinations. The invention can be practiced with polyamides regardless of the polymer morphology. Amorphous, semicrystalline or highly

crystalline polyamides as well as blends of different crystallinity are benefited. Commercially available polyamide resins are known from sources such as BASF, DSM, Evansville, Ind., E I duPont de Nemours, Wilmington, De.; formulated polyamides are available, for example, from Ferro Corp., Cleveland, Ohio, Hanna Engineered Materials, Bethlehem, Pa., Hüls America, Somerset, N.J., and A. Schulman, Akron, Ohio; reinforced polyamides are available from DSM RIM Nylon, Westlake, Ohio.

[0018] The following amounts of each component selected according to the invention are critical to synergistic improvements and are indicated as weight percentage representing grams of additives used per hundred parts of the polyamide. The invention can be practiced by incorporating the additive system directly into heated zones of a compounding extruder containing the polyamide to be stabilized or by first forming an intermediate masterbatch compound which contains the selected system in a carrier polymer which is a polyamide or a polymer which is intimately compatible with or dispersible in polyamide, or by other methods commonly used in the art to incorporate additives into polymers.


[0019] The aromatic di-carbonyl (ester)amide compound is used generally in an amount of from 0.05% to 5%, preferably from 0.2% to 2% and most preferably from 0.3% to 1%.

[0020] The sterically hindered phenyl phosphonites used herein have the following general structure:




wherein each R is independently selected from unsubstituted phenyl or a substituted phenyl with one, two or three C₁₋₁₂alkyl groups, such as methyl, ethyl, propyl, butyl, isobutyl, tert.-butyl groups, linear or branched pentyl, hexyl, octyl or nonyl groups or cumyl moieties. Preferably R is a di-tert.-butyl phenyl group (most preferably at the 2,4-position), n is 0 or 1 and A is a predominantly aromatic mono- or difunctional C₅ to C₃₀ moiety optionally containing further heteroatoms, for example is a monofunctional or difunctional residue of a phenyl, diphenylether, diphenyl, diphenylmethane, or dibenzofuran group. Most preferably A is a diphenyl residue, n = 1 and R is a 2,4-di-tert-butyl phenyl group or 2,4-di-tert-butyl-5-methyl phenyl group. The term "sterically hindered" refers to the presence of at least one substituent different from hydrogen, in ortho position to the functional center of the respective group.

[0021] The most preferred phenyl phosphonites are the condensation products of sterically hindered alkyl phenols, such as 2,4-di-tertiary butyl phenol, with the Friedel-Crafts reaction product of diphenyl and PCl₃. An exemplary condensation product A-2 has the following structure:




[0022] The preferred sterically hindered phosphonite containing A-2 as main component is Sandostab® P-EPQ available from Clariant.

[0023] The oxalic acid di-aryl amides (oxanilides) used in the invention include, for example, compounds having the following structures:






R_1 and R_2 are each independently of the other hydrogen, unsubstituted C_1 - C_{18} alkoxy or C_1 - C_{18} alkoxy which is substituted by halogen, hydroxy, C_1 - C_5 alkoxy, carboxyl groups, carbamyl groups or C_1 - C_{12} alkoxy carbonyl groups, or is C_3 - C_5 alkenyloxy, unsubstituted benzyloxy or benzyloxy which is substituted by halogen or C_1 - C_5 alkyl, aliphatic acyloxy containing up to 18 carbon atoms, unsubstituted benzoyloxy or benzoyloxy which is substituted by halogen or C_1 - C_4 alkyl, or a radical $-A-SO_3M$, wherein A is a direct bond or a divalent radical of formula $-O-Q-$, and Q is unsubstituted or hydroxy-substituted C_1 - C_6 alkylene, M is hydrogen or alkali metal, R_3 and R_4 are each independently of the other hydrogen, halogen, C_1 - C_{12} alkyl, haloalkyl, phenyl or phenyl- C_1 - C_5 alkyl, or two radicals R_3 and/or R_4 in ortho-position each together form a fused 6-membered aromatic carbon ring, and wherein m and n are 1 or 2 and p and q are 1, 2 or 3. The preferred oxalic acid di-aryl amide is non-hydroxy substituted, for example:



wherein R_1 and R_2 are each independently, identical or different substituents selected from hydrogen, linear, branched or cyclic alkyl or alkoxy groups having from 2 to 12 carbon atoms and from 1 to 4 oxygen atoms; preferably one R_1 group on each ring is hydrogen, one R_2 group is ethoxy and the other is a C_2 to C_{12} alkyl group, both located at the 5 position of each ring.

[0024] The most preferred oxanilides have such structures as:






[0025] Commercially available non-hydroxyl substituted oxanilides include Sanduvor® VSU and 3206, and Tinuvin® 312 and 315, and the like. The most preferred oxanilide is commercially available from Clariant as Sanduvor® VSU.

[0026] Examples of alkyl groups having not more than 20 carbon atoms are methyl, ethyl, propyl, isopropyl, butyl, 2-butyl, isobutyl, t-butyl, pentyl, 2-pentyl, hexyl, heptyl, octyl, 2-ethylhexyl, t-octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, hexadecyl and octadecyl; exemplary branched alkyl groups are isopropyl, isobutyl, t-butyl, 2,2-dimethylpropyl, 2-methylpropyl, cyclohexylmethyl, cyclohexylethyl, 2-ethylhexyl, 3,5,5-trimethylhexyl, 2-hexylundecyl, and 5,7,7-trimethyl-2-(1,3,3-trimethylbutyl)hexyl; exemplary cyclic alkyl groups are cyclohexyl.

[0027] Examples of alkoxy(alkyl) groups are methoxy, ethoxy, propoxy, isopropoxy, butoxy, isobutoxy, pentoxy, isopentoxy, hexoxy, 2-ethylhexyloxy, heptoxy, octoxy, decyloxy, dodecyloxy, tetradecyloxy, hexadecyloxy and octadecyloxy, nonadecyloxy. Preferred alkoxy examples are C₆-C₁₂alkoxy, in particular heptoxy and octoxy.

[0028] Examples of the alkoxyalkylenoxyalkyl groups are C₁₋₂₀-alkoxy-C₁₋₅-alkylenoxy-C₁₋₂₀-alkyl groups. The C₁₋₂₀-alkoxy groups and C₁₋₂₀-alkyl groups include those mentioned as examples of the alkoxyalkyl groups. Examples of the C₁₋₅-alkylenoxy groups include -CH₂O-, -CH₂CH₂O-, -CH₂CH₂CH₂O-,



[0029] Particularly, C₁₋₁₂-alkoxy-C₁₋₅-alkylenoxy-C₁₋₁₂-alkyl groups are more preferred.

[0030] Examples of C₅-C₁₂cycloalkyl R₃ unsubstituted or mono-, di- or tri-substituted by C₁-C₄alkyl are cyclopentyl, methylcyclopentyl, dimethylcyclopentyl, cyclohexyl, methylcyclohexyl, dimethylcyclohexyl, trimethylcyclohexyl, t-butylcyclohexyl, cyclooctyl, cyclodecyl and cyclododecyl. Unsubstituted or substituted cyclohexyl is preferred.


[0031] Examples of C₅-C₁₂cycloalkoxy R₁ are cyclopentoxy, cyclohexoxy, cycloheptoxy, cyclooctoxy, cyclodecyloxy and cyclododecyloxy, including as applied to R₃. Cyclopentoxy and cyclohexoxy are preferred.

[0032] Examples of C₃-C₆ alkenyl are allyl, 2-methylallyl, butenyl and hexenyl, 3-butenyl, and 10-undecenyl; examples of branched alkenyl groups are 1-methyl-2-propenyl, 3-methyl-3-butenyl. Allyl is preferred.

[0033] Examples of C₇-C₉ phenylalkyl unsubstituted or mono-, di- or tri-substituted on the phenyl by C₁-C₄alkyl are benzyl, methylbenzyl, dimethylbenzyl, trimethylbenzyl, t-butylbenzyl and 2-phenylethyl. Benzyl is preferred.

[0034] Examples of aliphatic and aromatic C₁-C₁₀ acyl are C₁-C₈alkanoyl or C₃-C₈-alkenoyl, for example, acetyl, propionyl, butyryl, isobutyryl, pentanoyl, benzoyl, hexanoyl, heptanoyl, octanoyl, 2-ethylhexanoyl, acryloyl and crotonyl. Acetyl is preferred.

[0035] The most preferred aromatic (ester) amide is an aromatic di-amide having the following structure:



and is commercially available as NYLOSTAB S-EED from Clariant.

[0036] Conventional additives may optionally be present in the polyamide which is modified according to the invention, for example, primary thermal stabilizers, light stabilizers, lubricants, pigments, reinforcing and/or non-reinforcing fillers, and the like. Conventional primary antioxidants are suggested for inclusion herein at conventional amounts. Antioxidants include, for example alkylated monophenols, alkylated hydroquinones, alkylidenebisphenols, hindered alkyl benzyl compounds, acylaminophenols, esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl) propionic acid, and the like which are disclosed in U.S. Pat. No. 5,051,459 incorporated herein by reference. A commercially available antioxidant is IRGANOX® 1098 from Ciba Specialty Chemicals.

[0037] UV-absorbers include, for example, the class of benzotriazoles such as 2-(2'-hydroxyphenyl)benzotriazoles, for example 2-(2'-hydroxy-5'-methylphenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(5'-tert-butyl-2'-hydroxyphenyl)-benzotriazole, 2-[2'-hydroxy-5'-(1,1,3,3-tetramethylbutyl)phenyl]benzotriazole, 2-(3'-5'-di-tert-butyl-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-methyl-phenyl)-5-chlorobenzotriazole, 2-(3'-sec-butyl-5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-4'-octyloxy-phenyl)benzotriazole, 2-(3',5'-di-tert-amyl-2'-hydroxy-phenyl)-benzotriazole, 2-(3',5'-bis(θ , θ -dimethylbenzyl)-2'-hydroxyphenyl)benzotriazole; mixture of 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxy-carbonyl-ethyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethyl-hexyloxy)carbonyl-ethyl]-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonyl-ethyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonyl-ethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-(2-octyloxy-carbonyl-ethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethyl-hexyloxy)carbonyl-ethyl]-2'-hydroxyphenyl)-benzotriazole, 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)-benzotriazole, and 2-(3'-tert-butyl-2'-hydroxy-5'-(2-isooctyloxy-carbonyl-ethyl)-phenyl)benzotriazole, 2,2'-methylenebis[4-(1,1,3,3-tetramethylbutyl)-6-benzotriazol-2-ylphenol]; transesterification product of 2-[3'-tert-butyl-5'-(2-methoxycarbonyl-ethyl)-2'-hydroxyphenyl]benzotriazole with polyethylene glycol 300; $[R-CH_2CH_2-COO(CH_2CH_2)_3]_2$ where $R = 3'$ -tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-yl-phenyl; $[R-CH_2CH_2-COO(CH_2CH_2O)_n]_2$ where $n = 1$ to 5 and $R = 3'$ -tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-yl-phenyl. A suitable commercially available benzotriazole is Norbloc® 7966, and 6000, from Jensen Pharma., Inc. Benzotriazoles are disclosed in U.S. Pats. 4,335,155, 4,405,749, and 4,528,311 which are incorporated herein by reference.

[0038] Further UV-absorbers include the class of ortho-hydroxyphenyl triazines such as 2-(2-hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxy-phenyl)-4,6-bis-(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methyl-phenyl)-1,3,5-triazine, 2-(2-hydroxy-4-dodecycloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-butyloxypropyloxy)phenyl]-4,6-bis(2,4-di-methylphenyl)-1,3,5-triazine and 2-hydroxy-4-(2-hydroxy-3-octyloxypropyloxy)-phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine. A suitable commercially available triazine is CYASORB® 1164, from Cytec Corp.

[0039] Hindered benzoate UV-absorbers include commercially available materials such as CYASORB® 2908 from Cytec, and FERRO® AM 340 from Ferro Corp.

[0040] Further, in this specification, where a range is given, the figures defining the range are included therein.

[0041] Further, any group capable of being linear, branched or cyclic is linear, branched or cyclic.

[0042] For the avoidance of doubt, in this specification tert-butyl means tertiary butyl or $C(CH_3)_3$.

[0043] The following examples illustrate the invention in its various aspects. All parts and percentages are expressed by weight, representing grams of additives used per hundred grams of polyamide.

EXAMPLES

[0044] In the comparative examples and in the exemplary non-limiting embodiments of the invention described hereunder, the following types of polyamide-based polymers and additives are used:


1) PA-1 A polyamide 6 of the low viscosity type suitable especially for injection molding and commercially available as Capron® 8202 NL from Allied Signal Corp.

2) PA-2 A transparent, amorphous, polyamide-polyether block copolymer suitable for injection molding and commercially available from EMS-CHEMIE, Domat/Ems, Switzerland.


3) PA-3 A semi-gloss polyamide 6 containing 0.3 wt.% of TiO₂ commercially available as Nylon 6 SD 1130 from DSM.

4) PS-1 A sterically hindered phosphonite processing stabilizer commercially available as Sandostab® P-EPQ from Clariant, Muttenz, Switzerland.

5) PS-2 A primary hindered phenolic antioxidant commercially available as Irganox® 1098 from Ciba Specialty Chemicals, Basle, Switzerland and which has the following structure:




6) PS-3 An antioxidant which is a compound of the following formula:




PS-3 is commercially available as Irganox® MD 1024 from Ciba Specialty Chemicals, Basle, Switzerland.


7) LS-1 A non-hydroxyl substituted oxanilide UV-absorber commercially available as Sanduvor® VSU from Clariant, having the following structure:




8) LS-2 An aromatic hindered piperidine UV-stabilizer commercially available as Nylostab® S-EED from Clariant, and which is a compound of the following formula:




9) LS-3 A UV-stabilizer which is commercially available as Tinuvin (RTM) 770 from Ciba Specialty Chemicals in Basle, Switzerland and which is a compound of the following formula:




10) LS-4 A UV-stabilizer which is commercially available as Chimassorb (RTM) 944 from Ciba Specialty Chemicals in Basle, Switzerland or as Sanduvor (RTM) 3944 from Clariant in Muttenz, Switzerland and which is a compound of the following formula:



11) LS-5 A UV-absorber which is commercially available as TINUVIN® 234 from Ciba Specialty Chemicals in Basle, Switzerland and which is a compound of the following formula:



12) LS-6 A UV-absorber which is commercially available as TINUVIN® 327 from Ciba Specialty Chemicals, Basle, Switzerland and which is a compound of the following formula:



[0045] The tested samples were prepared as follows. According to the formulations described hereunder, the different types of polyamides were first melt compounded with the tested additives and extruded at temperatures of from 250-280° Celsius, followed by pelletizing into homogeneous pellets. These pellets were formed into panels 1 mm thick by injection molding at temperatures of from 280 to 300° Celsius, followed by either punching of the tested samples to 35 mm x 40 mm or by direct injection molding of tensile bar specimens.

[0046] The color determination is reported in terms of the Yellowness Index (YI) determined in accordance with the ASTM E-313 Yellowness Test. The higher the value, the lower the color quality, i.e. the stronger the discoloration.

[0047] In addition, the color is measured according to the regulations of the CIE (International Commission on Illumination) and in accordance with the ISO 7724/3 and DIN 6174 standards. The higher the positive value of b^* , the more pronounced the yellowing.

[0048] The tensile strength is measured in accordance with the ASTM D-638 standard.

[0049] The accelerated weathering test (Atlas WOM 65 WRC) is carried out according to the DIN 53387-A standard.

[0050] The results of the tests carried out with stabilizer compositions according to the invention and with stabilizers according to the prior art (for comparative purposes) applied to different types of polyamides are summarized in the tables 1-3.

TABLE 1

Yellowness index and b^* -value of the various formulations containing PA-1 as polymer after processing into the tested samples.

No.	Formulation	Yellowness Index	b^* -value
1	Ref. Sample	1.36	0.61
2	0.1 % PS-1	0.71	0.31
3	0.5 % LS-1	4.03	1.79
4	0.1 % / 0.5% of PS-1 / LS-1	-2.42	-1.06
5	0.5 % LS-2	3.87	1.70
6	0.1% / 0.5% of PS-1 / LS-2	-4.57	-1.98
4	0.5 % LS-5	17.20	7.86
8	0.1 % / 0.5% of PS-1 / LS-5	15.07	6.85
9	0.5 % LS-5	14.29	6.52
10	0.1% / 0.5% of PS-1 / LS-6	12.96	5.88

[0051] Test numbers 4 and 6 of table 1 are formulations according to the invention; test numbers 7-10 of table 1 are comparative tests.

[0052] The effect of the processing stabilizer PS-1 to improve the values of yellowing can be seen from the results shown in table 1. From the data of this table it can also be gathered that the preferable use of the UV-stabilizers LS-1

and LS-2 is clearly appropriate, although up to now some minor worsening had to be accepted in the preparation of light-stabilized polyamides.

[0053] Therefore, the synergism observed with the stabilizer composition according to the invention is totally unexpected. In spite of the high thermal stress during the processing of the polyamides into the tested samples, yellowing does not occur at all. The measured values of the Yellowness Index and of the b^* -value do not only achieve the level of the reference sample but exceed the quality of the reference sample in a significant manner.

[0054] The comparative tests show that the use of the processing stabilizer PS-1 in combination with other light stabilizers than those according to the invention, such as LS-5 and LS-6 lead only to minor improvements of the yellowing values which are generally increased versus the reference as soon as a light stabilizer is present in the matrix to be stabilized. The synergism caused by the stabilizer composition according to the invention is not observed in other cases, i.e. the synergism is limited to the composition according to the invention only.

TABLE 2

Tensile strength (TS) and b^* -value of various formulations containing PA-2 as polymer after exposure to accelerated weathering (WOM 65 WRC) for 1800 hours.

No.	Formulation, always with 0.2% PS-2	b^* -value	TS (% of the original value)
1	Reference sample	7.85	29
2	0.6 % LS-1	4.04	84
3	0.6 % LS-2	4.71	39
4	0.6 % LS-3	4.65	49
5	0.6 % LS-4	5.40	40
6	0.3 % / 0.3 % of LS-1 / LS-2	2.62	96
7	0.3 % / 0.3 % of LS-1 / LS-3	3.05	88
8	0.3 % / 0.3 % of LS-1 / LS-4	3.58	82

[0055] Test number 6 of table 2 is a formulation according to the invention; test numbers 7 and 8 of table 2 are comparative tests.

[0056] If light stabilizers are not used the weathering causes a markedly increase of the yellowing value as well as a distinct worsening of the mechanical properties of PA-2 (cf. reference sample). Further, the data of table 2 shows that the high efficacy of the UV-stabilizer LS-1 exceeding clearly the effectiveness of the UV-stabilizers LS-2, LS-3 and LS-4 in view of the yellowing value b^* and the tensile strength. As it is obvious from table 2, the combination of LS-1 and LS-2 surprisingly results in a pronounced synergism enabling the production of polyamides having a markedly improved light fastness, i.e. resistance against yellowing, as well as a better UV-fastness, i.e. retention of the mechanical properties.

TABLE 3

Table 3 illustrates b^* -values and condition of the tested samples containing PA-3 as polyamide after exposure to accelerated weathering (WOM 65 WRC) at the time indicated.

	Formulation always with 0.25 wt. % PS-2	b^* - value	Time of embrittlement
1	reference sample	n.d. ¹	3000 h
2	0.5% / 0.25% LS-1 / LS-2	2.6	> 4000 h
3	0.5% / 0.25% LS-1 / LS-3	n.d. ¹	3000 h
4	0.5% / 0.25% LS-1 / LS-4	3.3	> 4000 h
5	0.5% / 0.25% LS-5 / LS-2	5.6	> 4000 h
6	0.5% / 0.25% LS-5 / LS-3	4.6	> 4000 h
7	0.5% / 0.25% LS-5 / LS-4	4.7	> 4000 h

n.d.¹ sample decomposed- not measurable


[0057] Test number 2 of Table 3 is a formulation according to the invention; test numbers 3 to 7 of Table 3 are comparative tests.

[0058] In this test series, samples were exposed to accelerated weathering for up to 4000 hours followed by meas-

urement of b*-yellowing, and evaluation of embrittlement. The stabilized polyamide containing LS-1 with LS-2 according to the invention showed outstanding efficiency with regard to yellowing resistance and retention of mechanical properties. The stabilizer combination No. 2 of LS-1/LS-2 far out-performed those combinations of LS-1/LS-3 and LS1/LS-4 and accordingly any combinations of LS-5 evidencing an unexpected and unique result.


Claims

1. A process for stabilizing polyamide polymers against the damage effected by light, heat and/or oxidation comprising incorporating therein by melt-processing a synergistic additive system resulting in a uniform and intimate mixture with said polyamide, said additive system is from 0.01% to 1% by weight of a sterically hindered phenyl phosphonite, from 0.05% to 5% by weight of an oxanilide and from 0.05% to 5% by weight of an aromatic di-carbonyl compound of the formula




and wherein the percentages represent grams of additives used per hundred grams of polymer.

2. The process according to claim 1 wherein said sterically hindered phenyl phosphonite has the following structure:




wherein each R is independently unsubstituted phenyl or a substituted phenyl with one, two or three alkyl groups each having from 1 to 12 carbon atoms or a substituted phenyl with one or two cumyl groups, n is 0 or 1, and A is a predominantly aromatic, mono- or difunctional C₅-C₃₀ moiety optionally containing further heteroatoms.

3. The process according to claim 1 wherein said oxanilide has the following structure:




R_1 and R_2 are each independently of the other hydrogen, unsubstituted C_1 - C_{18} alkyl or C_1 - C_{18} alkoxy which is substituted by halogen, hydroxy, C_1 - C_5 alkoxy, carboxyl groups, carbamyl groups or C_1 - C_{12} alkoxycarbonyl groups, or is C_3 - C_5 alkenyloxy, unsubstituted benzyloxy or benzyloxy which is substituted by halogen or C_1 - C_5 alkyl, aliphatic acyloxy containing up to 18 carbon atoms, unsubstituted benzoyloxy or benzoyloxy which is substituted by halogen or C_1 - C_4 alkyl, or a radical of formula $-A-SO_3M$, wherein A is a direct bond or a divalent radical of formula $-O-Q-$, and Q is unsubstituted or hydroxy-substituted C_1 - C_6 alkylene, M is hydrogen or alkali metal, R_3 and R_4 are each independently of the other hydrogen, halogen, C_1 - C_{12} alkyl, haloalkyl, phenyl or phenyl- C_1 - C_5 alkyl, or two radicals R_3 and/or R_4 in ortho-position each together form a fused 6-membered aromatic carbon ring, and wherein m and n are 1 or 2 and p and q are 1, 2 or 3.

4. The process according to claim 3 wherein said oxanilide has the following structure:




wherein R_1 and R_2 are each independently, identical or different moieties selected from hydrogen, linear, branched or cyclic alkyl or alkoxy groups having from 2 to 12 carbon atoms and from 1 to 4 oxygen atoms.

5. The process according to claim 1 wherein the sterically hindered phenyl phosphonite comprises a reaction product of the condensation of a hindered alkylphenol with the Friedel-Crafts-reaction product of biphenyl and PCl_3 , the aromatic di-carbonyl compound has the structure:



and the non-hydroxyl substituted oxanilide has the following structure:




wherein R_1 and R_2 are each independently, identical or different substituents selected from hydrogen, linear or branched alkyl or alkoxy groups having from 2 to 12 carbon atoms and from 1 to 4 oxygen atoms.

6. A polyamide article selected from the group consisting of molded articles, extruded articles and fibers which comprise polyamide, optionally an organic dye, and in intimate homogeneous mixture therewith, an additive system as defined in claims 1 to 5.


Patentansprüche

1. Verfahren zum Stabilisieren von Polyamidpolymeren gegen Schädigung durch Licht, Wärme und/oder Oxidation, umfassend das Einbringen durch ein Schmelzverfahren eines synergistischen Additivsystems darin, wodurch sich ein gleichmässiges und inniges Gemisch mit dem Polyamid ergibt, wobei das Additivsystem 0,01 Gew.-% bis 1 Gew.-% eines sterisch gehinderten Phenylphosphonits, 0,05 Gew.-% bis 5 Gew.-% eines Oxanilids und 0,05 Gew.-% bis 5 Gew.-% einer aromatischen Dicarbonylverbindung der Formel




umfasst und wobei die Prozente Gramm der pro 100 Gramm Polymer verwendeten Additive darstellen.

2. Verfahren nach Anspruch 1, wobei das sterisch gehinderte Phenylphosphonit die folgende Struktur besitzt:



wobei jedes R unabhängig unsubstituiertes Phenyl oder ein mit einer, zwei oder drei Alkylgruppen mit jeweils 1 bis 12 Kohlenstoffatomen substituiertes Phenyl oder ein mit einer oder zwei Cumylgruppen substituiertes Phenyl ist, n 0 oder 1 ist und A eine vorwiegend aromatische, mono- oder difunktionelle C₅-C₃₀-Einheit ist, die gegebenenfalls weitere Heteroatome enthält.


3. Verfahren nach Anspruch 1, wobei das Oxanilid die folgende Struktur besitzt:



R₁ und R₂ sind jeweils unabhängig voneinander Wasserstoff, unsubstituiertes C₁-C₁₈-Alkoxy oder C₁-C₁₈-Alkoxy, das mit Halogen, Hydroxy, C₁-C₅-Alkoxy, Carboxylgruppen, Carbamylgruppen oder C₁-C₁₂-Alkoxy-carbonylgruppen substituiert ist oder C₃-C₅-Alkenyloxy, unsubstituiertes Benzoyloxy oder Benzoyloxy, das mit Halogen oder C₁-C₅-Alkyl, aliphatischem Acyloxy mit bis zu 18 Kohlenstoffatomen substituiert ist, unsubstituiertes Benzoyloxy oder Benzoyloxy ist, das mit Halogen oder C₁-C₄-Alkyl oder einem Rest der Formel -A-SO₃M substituiert ist, wobei A eine direkte Bindung oder ein zweiwertiger Rest der Formel -O-Q- ist und Q unsubstituiertes oder hydroxysub-


stituiertes C₁-C₆-Alkylen ist, Wasserstoff oder Alkalimetall bedeutet, R₃ and R₄ je unabhängig voneinander Wasserstoff, Halogen, C₁-C₁₂-Alkyl, Halogenalkyl, Phenyl oder Phenyl-C₁-C₅-Alkyl sind oder zwei Reste R₃ und/oder R₄ in ortho-Position zueinander einen kondensierten, 6-gliedrigen, aromatischen Kohlenstoffring bilden und wobei m und n 1 oder 2 und p und q 1, 2 oder 3 sind.

4. Verfahren nach Anspruch 3, wobei das Oxanilid die folgende Struktur besitzt:




wobei R₁ und R₂ jeweils unabhängig identische oder verschiedene Einheiten sind, die aus Wasserstoff, geraden, verzweigten oder cyclischen Alkyl- oder Alkoxygruppen mit 2 bis 12 Kohlenstoffatomen und 1 bis 4 Sauerstoffatomen ausgewählt sind.

5. Verfahren nach Anspruch 1, wobei das sterisch gehinderte Phenylphosphonit ein Reaktionsprodukt aus der Kondensation eines gehinderten Alkylphenols mit dem Friedel-Crafts-Reaktionsprodukt von Biphenyl und PCl₃ umfasst, die aromatische Dicarbonylverbindung die Struktur hat:



und das nicht hydroxylsubstituierte Oxanilid die folgende Struktur hat:




wobei R₁ und R₂ jeweils unabhängig identische oder verschiedene Substituenten sind, die aus Wasserstoff, geraden oder verzweigten Alkyl- oder Alkoxygruppen mit 2 bis 12 Kohlenstoffatomen und 1 bis 4 Sauerstoffatomen ausgewählt sind.

6. Polyamidgegenstand, der aus der Gruppe ausgewählt ist, die aus geformten Gegenständen, extrudierten Gegenständen und Fasern besteht, die Polyamid, gegebenenfalls einen organischen Farbstoff und, in einem innigen homogenen Gemisch damit, ein Additivsystem nach den Ansprüchen 1 bis 5 umfassen.


Revendications

1. Procédé de stabilisation de polymères polyamides vis-à-vis des dommages induits par la lumière, la chaleur et/ou l'oxydation, comprenant l'incorporation dans ceux-ci par traitement par fusion d'un système additif synergique, dont il résulte un mélange uniforme et intime avec ledit polyamide, ledit système additif se compose de 0,01 % à 1 % en poids d'un phosphonite de phényle stériquement encombré, de 0,05 % à 5 % en poids d'un oxanilide et de 0,05 % à 5 % en poids d'un composé aromatique dicarboxylé de formule :




et dans lequel les pourcentages représentent des grammes d'additifs utilisés pour cent grammes de polymère.

2. Procédé selon la revendication 1 dans lequel le phosphonite de phényle stériquement encombré a la structure suivante :



dans laquelle chaque R est indépendamment un phényle non substitué ou un phényle substitué par un, deux ou trois groupes alkyle ayant chacun de 1 à 12 atomes de carbone ou un phényle substitué par un ou deux groupes cumyle, n vaut 0 ou 1, et A est un motif en C₅-C₃₀ principalement aromatique, mono ou difonctionnel contenant éventuellement d'autres hétéroatomes.


3. Procédé selon la revendication 1 dans lequel ledit oxanilide a la structure suivante :



dans laquelle R₁ et R₂ sont chacun indépendamment l'un de l'autre un hydrogène, un alcoxy en C₁-C₁₈ non substitué ou un alcoxy en C₁-C₁₈ qui est substitué par un halogène, un hydroxy, un alcoxy en C₁-C₅, des groupes carboxyle, des groupes carbamyle ou des groupes alcoxycarbonyle en C₁-C₁₂, ou sont un alcényloxy en C₃-C₅, un benzyloxy non substitué ou un benzyloxy qui est substitué par un halogène ou un alkyle en C₁-C₅, un acyloxy


aliphatique contenant jusqu'à 12 atomes de carbone, un benzyloxy non substitué ou un benzyloxy qui est substitué par un halogène ou un alkyle en C₁-C₄, ou un radical de formule -A-SO₃M, dans laquelle A est une liaison directe ou un radical bivalent de formule -O-Q-, et Q est un alkylène en C₁-C₆ non substitué ou substitué par un hydroxy, M est un hydrogène ou un métal alcalin, R₃ et R₄ sont chacun indépendamment l'un de l'autre un hydrogène, un halogène, un alkyle en C₁-C₁₂, un haloalkyle, un phényle ou un phénylalkyle en C₁-C₅, ou deux radicaux R₃ et/ou R₄ chacun en position ortho forment ensemble un cycle aromatique à 6 atomes de carbone fusionné, et dans laquelle m et n valent 1 ou 2 et p et q valent 1, 2 ou 3.

4. Procédé selon la revendication 1 dans lequel ledit oxanilide a la structure suivante :




dans laquelle R₁ et R₂ sont chacun indépendamment, des motifs identiques ou différents choisis parmi un hydrogène, des groupes alkyle ou alcoxy linéaires, ramifiés ou cycliques ayant de 2 à 12 atomes de carbone et de 1 à 4 atomes d'oxygène.

5. Procédé selon la revendication 1 dans lequel ledit phosphonite de phényle stériquement encombré, comprend un produit de réaction de la condensation d'un alkylphénol encombré avec le produit de la réaction de Friedel-Crafts du diphenyle avec PCl₃, le composé aromatique dicarbonylé a la structure :



et l'oxanilide non hydroxylé a la structure suivante :



dans laquelle R₁ et R₂ sont chacun indépendamment, des substituants identiques ou différents choisis parmi un hydrogène, des groupes alkyle ou alcoxy linéaires ou ramifiés ayant de 2 à 12 atomes de carbone et de 1 à 4 atomes d'oxygène.

6. Article de polyamide choisi dans le groupe consistant en des articles moulés, des articles extrudés et des fibres qui comprennent un polyamide, éventuellement un colorant organique, et en mélange homogène intime avec celui-ci, un système additif tel que défini dans les revendications 1 à 5.